



AMENDMENTS TO THE SPECIFICATION

Please replace the table at page 14, with the following rewritten table:

Ex.	Emulsifiers	HLB	Solids content [%]	PH	Dynamic viscosity [mPa*s]	Particle size r_{ns} [nm]	Coagulum content [%]	Crystallization of the emulsifier
6	Polyoxyethylene-100-isononylphenol	19.1	50.4	2.5	6800	81	<0.5	yes
7	Polyoxyethylene-100-stearyl ether	18.8	50.6	2.4	760	88	n.d.	yes
8	Polyoxyethylene-50-nonylphenol	18.3	50.2	2.7	1225	76	0.04	yes
9	Polyoxyethylene-35-nonylphenol	17.5	51.7	n.d.	n.d.	72	0.1	yes
10	Polyoxyethylene-25-cetyl stearate	16.2	48.7	2.6	200	77	0.2	no
11	Polyoxyethylene-20-sorbitan monopalmitate	16.0	45.5	2.7	n.d.	112	n.d.	no
12	Polyoxyethylene-16-tert-octylphenol	15.8	50.6	2.5	2800	90	0.06	no
13	Polyoxyethylene-20-cetyl ether	15.7	50.5	2.5	350	82	0.06	no
14	Polyoxyethylene-20-sorbitan monostearate	15.6 14.9	n.d.	n.d.	n.d.	n.b.	>10	n.d.*
15	Polyoxyethylene-20-sorbitan monooleate	15.3 15.0	47.7	2.6	480	91	8.21	n.d.*